

## TECHNICAL SPECIFICATIONS:

# TUF BOARD®

### I. TYPICAL PROPERTIES (Based on 19 mm)

PROPERTY	TEST METHOD	UNIT	VALUE
<b>PHYSICAL</b>			
Specific Gravity	ASTM D 792	g/cm <sup>3</sup>	0.55
Shore D Hardness	ASTM D 2240	D	60
<b>MECHANICAL</b>			
Flexural Strength @ Yield	ASTM D 790	psi	2,000
Flexural Modulus	ASTM D 790	psi	110,000
Nail Withdraw	ASTM D 1761	lbf/in	60
Screw Withdraw	ASTM D 1761	lbf/in	485
<b>THERMAL</b>			
Heat Distortion Temperature	ASTM D 648	°F	140
Coefficient of Linear Expansion	ASTM D 696	in/in/°F	2.5 x 10 <sup>-5</sup>
Thermal Conductivity	ASTM C 177	W/m °K	0.06

### II. FLAMMABILITY STANDARDS

OTHER PROPERTY		RATING
UL 94	V0	Passed
UL 94	5V	Passed
UL 94	HB	Passed

### III. AVAILABILITY

	STANDARD	CUSTOM
SIZE	4 ft x 8 ft (48" x 96")	Available upon request
COLOR	Tan	Available upon request
GAUGES (in millimeters)	19	Available upon request

The information contained herein is true and accurate to the best of our knowledge. All recommendations and suggestions are made without guarantees. This information is to be used by individuals with technical skill at their own discretion and risk. Because conditions of use are beyond our control, World-Pak Division, Inteplast Group, Ltd. makes no warranties, expressed or implied, and assumes no liability in connection with the use of this information.

*Note: The above properties may vary slightly due to different sheet thickness.*

0706



**INTEPLAST GROUP, LTD.**  
WORLD-PAK DIVISION

PVC Sheet Business Unit  
9 Peach Tree Hill Road  
Livingston, NJ 07039  
Tel: 800-452-2117  
Fax: 800-889-8807